



World leaders in the conservation of man-made resources and the environment

# PRODUCT SPECIFICATION SHEET **BELZONA® 1812**

## 1. PRODUCT NAME

### Belzona® 1812

Coating for repairing and protecting surfaces against abrasive attack.

## 2. MANUFACTURER

### Belzona Inc.,

2000 N.W. 88th Court  
Miami, Florida 33172

### Belzona Polymerics Ltd.,

Claro Road, Harrogate,  
HG1 4AY, England.

## 3. PRODUCT DESCRIPTION

A two component system consisting of a base and solidifier. The product is based on high molecular weight polymers and oligomers incorporating abrasion resistant ceramic aggregates. This material may be applied from 1/8 inch (3 mm) to unlimited thickness onto horizontal or vertical surfaces. The system protects the substrate from abrasive attack and is ideally suited for application to:

- Pipe bends
- Chutes and hoppers
- Deflector screens
- Wear plates
- Centrifuges
- Mixing bowls

## 4. TECHNICAL DATA

### Base Component

Appearance	Granular thixotropic paste
Color	Grey
Density	2.2 - 2.4 g/cm <sup>3</sup>

### Solidifier Component

Appearance	Granular thixotropic paste
Color	Red
Density	2.0 - 2.2 g/cm <sup>3</sup>

### Mixed Components

Mixing Ratio by Weight (Base : Solidifier)	4.2 : 1
Mixing Ratio by Volume (Base : Solidifier)	4 : 1
Mixed Density	2.26 g/cm <sup>3</sup>
Useable Life at 70°F (22°C)	20-25 mins
at 50°F (10°C)	45-60 mins
Tack Free Time at 71°F (22°C)	4½ hours
at 50°F (10°C)	8 hours
Slump Resistance nil at 0.5 inch (12.7 mm)	

### • Shelf Life:

Separate base and solidifier components shall have a shelf life of at least 5 years when stored between 32°F (0°C) and 86°F (30°C).

### • Working Life:

Will vary according to temperature. At 77°F (25°C) the usable life of mixed material is 20 minutes.

### • Coverage Rate:

Each 1 kg applied at 1/8 inch (3 mm) thickness will cover approximately 1.58 sq.ft. (0.147 sq.m.).

### • Volume Capacity:

The volume capacity of mixed product is 27 cu.ins. (442 cc) per kg.

### • Cure Time:

Will be reduced for thicker sections and extended for thinner applications. At a thickness of approximately 1/4 in. (6 mm), allow to solidify for the times shown in the chart below before subjecting it to the conditions indicated.

## 5. PHYSICAL / MECHANICAL PROPERTIES

Determined after 7 days cure at 77°F (25°C).

### • Abrasion Resistance:

#### Taber

The Taber abrasion resistance with 1 kg load is typically:  
H10 Wheels (Wet) 74 mm<sup>3</sup>  
loss per 1000 cycles

### Impact Abrasion

Test consists of firing 2 kg of G34 chilled iron grit at 80 psi and 90° angle:

Belzona® 1812	volume loss 36 mm <sup>3</sup>
Basalt	volume loss 30 mm <sup>3</sup>

### • Adhesion:

#### Tensile Shear

When tested in accordance with ASTM D1002, typical values will be 2570 psi (181 kgs/cm<sup>2</sup>).

### • Chemical Resistance:

While specifically designed for dry heat abrasion resistance, exhibits excellent chemical resistance to most commonly found chemical substances including inorganic acids and bases.

### • Compressive Yield Strength:

When tested in accordance with ASTM D695, typical values obtained will be 13300 psi (935 kgs/cm<sup>2</sup>).

### • Flexural Strength:

When tested to ASTM D790, typical values obtained will be 8100 psi (570 kgs/cm<sup>2</sup>).

## CURE TIMES

TEMPERATURE	41°F (5°C)	50°F (10°C)	59°F (15°C)	68°F (20°C)	77°F (25°C)	86°F (30°C)
Movement or use involving no loading	18 hrs	8 hrs	6 hrs	4 hrs	3 hrs	2 hrs
Machining and/or light loading	24 hrs	12 hrs	9 hrs	6 hrs	4 hrs	3 hrs
Full mechanical or thermal loading	7 days	5 days	4 days	3 days	2 days	1½ days
Contact with chemicals	14 days	10 days	7 days	5 days	3 days	2 days

## • Heat Distortion

### Temperature:

Tested to ASTM D648 (264 psi fiber stress), typical values obtained will be 135°F (57°C). Post cured at 100°C: 185°F (85°C).

## • Heat Resistance:

For many typical applications of dry abrasion, the product is suitable up to 300°F (150°C).

## 6. SURFACE PREPARATION AND APPLICATION PROCEDURES

For proper technique, refer to the Belzona Instructions For Use leaflet which is enclosed with each packaged product.

## 7. AVAILABILITY AND COST

Belzona® 1812 is available from a network of Belzona® Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona® Distributor in your area.

## 8. WARRANTY

Belzona® guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona® Instructions For Use leaflet. Belzona® further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, etc.). Since Belzona® has no control over the use of the product described herein, no warranty for any application can be given.

## 9. TECHNICAL SERVICES

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

## 10. HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

**Belzona Polymerics Ltd.,**  
Claro Road,  
Harrogate, HG1 4AY,  
England.  
Tel: +44 (0) 1423 567641  
Fax: +44 (0) 1423 505967  
E-Mail: belzona@belzona.co.uk



BS EN ISO 9002 : 1994  
Certificate No. Q/09335



[www.belzona.com](http://www.belzona.com)

**Belzona Inc.,**  
2000 N.W. 88 Court,  
Miami, Florida 33172,  
U.S.A.  
Tel: +1 (305) 594 4994  
Fax: +1 (305) 599 1140  
E-Mail: belzona@belzona.com

Copyright © 2002 by Belzona International Limited. All rights reserved. Certain portions of this work copyright © 1998, 2001 by Belzona International Limited. No part of this work covered by the copyrights hereon may be reproduced or used in any form or by any means - graphic, electronic or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of the publisher.

Belzona® is a registered trademark

Printed in England 02/02 UK

Private and Confidential - For Internal Use Only



**Belzona® 1812 - Product Specification Sheet (2)**